



HIGH-TEMP RTV SILICONE

THERMOSEALANT™

HIGH-TEMP RTV SILICONE SEALANT

PROPERTIES:

Color	RED
Skin Time	6 minutes
Tack Free Time	15 minutes
Cure Time	1/8" bead per 24 hours
Elongation	500%
Hardness (Shore A)	30 +/- 5
Tensile Strength	350 psi
Extrusion Rate	335 g/min
Flow/Slump	None
Staining	None
UV Resistance	Excellent



SPECIFICATIONS:

Complies with FDA Regulation 21 CFR 177.2600.
Meets Federal Specification TT-S-001543A, TT-S-00230C, ASTM C920-86
NFS Standard 51

COLOR:

Red

SURFACE PREPARATIONS:

The substrate must be clean, dry, frost free, sound, and free of any oils, grease, or incompatible sealers, paints or coatings that may interfere with adhesion. Do not apply if surface is damp or contaminated. It is recommended all substrates are tested prior to application.

DIRECTIONS:

For best results, prepare a clean surface. Cut the nozzle to desired bead size. Apply with a caulking gun, forcing the sealant onto the substrate, then tool if needed. Clean excess material with mineral spirits similar solvent.

STORAGE:

Material is to be stored under controlled dry environment (below 75°F). Use within 18 months from date of manufacture. For best results, keep material in tightly closed containers when not in use.



THERMO MANUFACTURING INC.

Canton, OH44705 • U.S. & Canada Phone Toll Free: (888) 678-3709 • U.S. & Canada Fax Toll Free: (888) 678-8711 •

www.ThermoPan.com